

US009410261B2

(12) United States Patent

Hougham et al.

(54) TWO MASK PROCESS FOR ELECTROPLATING METAL EMPLOYING A NEGATIVE ELECTROPHORETIC PHOTORESIST

(71) Applicant: **GLOBALFOUNDRIES INC.**, Grand

Cayman (KY)

(72) Inventors: Gareth G. Hougham, Ossining, NY

(US); Gerard McVicker, Stormville, NY (US); Anna Pratt, Wallkill, NY

(US)

(73) Assignee: **GLOBALFOUNDRIES INC.**, Grand

Cayman (KY)

(*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 0 days.

(21) Appl. No.: 14/528,028

(22) Filed: Oct. 30, 2014

(65) **Prior Publication Data**

US 2015/0060266 A1 Mar. 5, 2015

Related U.S. Application Data

(62) Division of application No. 13/584,326, filed on Aug. 13, 2012.

(51)	Int. Cl.	
	C25D 17/12	(2006.01)
	G03F 7/20	(2006.01)
	G03F 7/00	(2006.01)
	C25D 1/00	(2006.01)
	C25D 5/02	(2006.01)
	C25D 13/00	(2006.01)

(52) U.S. Cl.

(58) Field of Classification Search

CPC		H01L 21/32
USPC	204/290	.01; 430/324
See application file for complete	e search l	nistory.

(45) Date of Patent:

(10) Patent No.:

US 9,410,261 B2

Aug. 9, 2016

(56) References Cited

U.S. PATENT DOCUMENTS

5,861,327 5,928,815 6,391,773 2011/0108316 2011/0111647	A B2 A1	7/1999 5/2002 5/2011	Andricacos et al. Hougham et al. Hougham H01L 21/486
2011/0111647 2011/0236833		5/2011 9/2011	439/884

OTHER PUBLICATIONS

Jeon, S. et al., "Fabricating Complex Three-Dimensional Nanostructures with High-Resolution Conformable Phase Masks" PNAS (Aug. 24, 2004) pp. 12428-12433, vol. 101, No. 34. Beuret, C. et al., "Microfabrication of 3D Multidirectional Inclined Structures by UV Lithography and Electroplating" IEEE Workshop on Micro Electro Mechanical Systems (Jan. 25-28, 1994) pp. 81-85. Notice of Allowance issued on Jan. 15, 2016 in U.S. Appl. No. 13/584,326.

* cited by examiner

Primary Examiner — Daborah Chacko Davis (74) Attorney, Agent, or Firm — Scully Scott Murphy and Presser

(57) ABSTRACT

A negative electrophoretic photoresist is applied over a plurality of protruding disposable template portions on a substrate. A silo structure is placed on planar portions of the negative electrophoretic photoresist that laterally surround the plurality of protruding disposable template portions. The negative electrophoretic photoresist is lithographically exposed employing the silo structure and a first lithographic mask, which includes a transparent substrate with isolated opaque patterns thereupon. After removal of the silo structure, the negative electrophoretic photoresist is lithographically exposed employing a second lithographic mask, which includes a pattern of transparent areas overlying the planar portions of the negative electrophoretic photoresist less the areas for bases of metal structure to be subsequently formed by electroplating. The negative electrophoretic photoresist is developed to form cavities therein, and metal structures are formed by electroplating within the cavities. The negative electrophoretic photoresist and the plurality of protruding disposable template portions can be subsequently removed.

15 Claims, 22 Drawing Sheets